

Primers and black paint produced with oxidised bitumen and selected pure solvents.

These products are suitable for sealing the porosity of concrete substrate and preparing a sound anchoring for multiple bituminous waterproofing coatings and bituminous membranes.

Ideal for anchoring hot-applied bituminous coatings on metal surfaces (oil and gas pipelines, water ducting, etc.).

Used for waterproofing and protection of cement and fibre cement construction elements as well as metal surfaces.



Società Italiana Bitumi e Affini s.r.l  
Via Giovanni Bovio, 28  
ITALY - 28100 Novara

 +39 0321 692687

 + 39 0321 692835

[www.sibabitumi.com](http://www.sibabitumi.com) · [siba@sibabitumi.com](mailto:siba@sibabitumi.com)



Scan me



PRIMERS  
BITUMINOUS BLACK PAINT



ROAD & INDUSTRIAL BITUMEN

## SIBA PRIMER

### SIBAPRIMER 80

To be applied on dry, clean surfaces.

### SIBAPRIMER 80 SD 30

Owing to its special additives, it can also be applied on damp surfaces.

### SIBAPRIMER 80 BA

Specially designed to adhere to damp metal surfaces.

### SIBAPRIMER 80 S

Specially designed for industrial use.

### SIBAPRIMER 80 RM

Specially designed for industrial use.

## BITOX SERIES

Made from oxidised bitumen of various grades, BITOX is suitable for the protection of metal structures (metal parts, tanks, gutters etc.), waterproofing and protection of cement and fibre cement construction elements, anchoring hot-applied bituminous coatings on metal surfaces such as oil and gas pipelines and water ducting.

The product can be applied with a brush, block brush, roller or airless, according to specific application and location requirements.

### PACKAGING

- 190 kg barrels
- 25 kg – 10 kg buckets

### STORAGE

12 months in original containers

## Technical Specifications

Type of bituminous black paint	Solid content by weight	Density 25°C	Ford Cup viscosity 4 mm Ø hole Temp. 25 °C	Drying times at 25 °C, RH 65%, wet film thickness 100 microns	
				dust free mins	touch dry mins
<b>SERIE SIBAPRIMER 80</b>					
STANDARD	50 ± 2	0,950 ± 0,030	20 ± 5	5	10
THICK	60 ± 2	0,945 ± 0,030	25 ± 10	3 ± 1	6 ± 4
<b>SERIE SIBAPRIMER 80 SD 30</b>					
	50 ± 2	0,945 ± 0,030	20 ± 10	6	12
<b>SERIE SIBAPRIMER 80 BA</b>					
	50 ± 2	0,940 ± 0,020	20 ± 5	5	10
<b>SERIE SIBAPRIMER 80 S*</b>					
	64 ± 2	0,970 ± 0,050	≥120	30	60
<b>SERIE SIBAPRIMER 80 RM*</b>					
	50 ± 2	0,910 ± 0,050	60 ± 10	50	180
<b>SERIE BITOX</b>					
100	50 ± 2	0,95	18 ± 5	6	15
100 RM	50 ± 2	0,900 ± 0,020	175 ± 55	50	240

\* available upon request

All pictures and technical data are only provided as a guide

